

Specification — Premium Safety Radiation Shielding Glass

— 5/64" (2.0mm) max lead equivalency

Lead glass is available in a variety of radiation shielding levels and serves as a viewing medium where clear visibility of the treatment area is required.

Laminated Lead Glass - Premium Safety Glazing

GENERAL:

Laminated lead glass is used to allow viewing the patient area while radiation is present and where a safety label is required by the application. The material is placed in a lead shielded frame to hold it in place in the wall.

PRODUCT DETAILS:

Lead Glass is a lead barium glass with more than 60 percent heavy metal oxide including at least 55 percent lead oxide (PbO). This glass is laminated to a 3mm layer of float glass using a PVB interlayer. This allows the glass to be shatter resistant.

It meets Federal Standard DD-G-451, Type 1, ANSI Z97.1-1984 and 16CFR1201 Cat. II. Both glass surfaces are mirror polished. This special quality glass is well-qualified to meet the high standards of stringent safety regulations established in the medical, scientific, as well as nuclear fields around the world.

This glass is permanently marked with the appropriate CPSC safety label.

EXECUTION:

Lead glass, cushioned by resilient materials, must be free to "float in the opening" (i.e., it

should have adequate clearance around all edges and laterally) so it does not directly touch the framing system.

Obtain compatible glazing sealant or glazing tape, setting blocks and edge blocking material from a local source. If the frame is fire labeled, check with the manufacturer for special glazing requirements. Glass should be set on two identical neoprene, EPDM, silicone or other compatible elastomeric setting blocks. Use spacers inside and out where local practice and job requirements dictate.

Provide edge blocking where local practice requires. Use compatible sealant or glazing tape. Clean only with a soft, non-abrasive cloth.

IMPORTANT - Check glass for damage immediately upon arrival at site.

NOTE: For fire-labeled or safety-glazed openings, special considerations apply. Interpretation of building and fire codes varies depending on locale. Consult with local authorities on the proper fire-rated or safety glazing procedures. Labeled wire glass or ceramic glazing such as Firelite™ must be used in the view window in conjunction with lead glass for labeled openings. LX-57B lead glass is available in a laminated form for safety glazing applications.

PROPERTIES	Lead Glass Type	
	14LG	
Thickness (mm) (Approx.)	14mm	
Thickness (in.) (Approx.)	9/16"	
Max. Lead Equivalent (mm)	2.0mm	
Max. Lead Equivalent (in.)	5/64"	
Densities (gm/cm)	4.36	
Weight (lbs/sq.ft)	10.4	
X-Ray Peak Voltage (kv)	150	
Refractive Index (Typ.)	1.79	
Transmission (500 - 600nm)	87.8%	
SIZE AND TOLERANCE:		
Minimum size	any size on request	
Maximum size	96" x 48" (2438.4mm x 1219.2 mm)	



268 Old Lindale Road
Rome, Georgia 30161

Phone Toll Free: 800-329-5323
 Fax Toll Free: 800-329-5320
 e-mail: alshield@alshielding.com
 Internet: www.alshielding.com

Specification — Premium Safety Radiation Shielding Glass

— 7/64" (3.0mm) max lead equivalency

Lead glass is available in a variety of radiation shielding levels and serves as a viewing medium where clear visibility of the treatment area is required.

Laminated Lead Glass - Premium Safety Glazing

GENERAL:

Laminated lead glass is used to allow viewing the patient area while radiation is present and where a safety label is required by the application. The material is placed in a lead shielded frame to hold it in place in the wall.

PRODUCT DETAILS:

Lead Glass is a lead barium glass with more than 60 percent heavy metal oxide including at least 55 percent lead oxide (PbO). This glass is laminated to a 3mm layer of float glass using a PVB interlayer. This allows the glass to be shatter resistant.

It meets Federal Standard DD-G-451, Type 1, ANSI Z97.1-1984 and 16CFR1201 Cat. II. Both glass surfaces are mirror polished. This special quality glass is well-qualified to meet the high standards of stringent safety regulations established in the medical, scientific, as well as nuclear fields around the world.

This glass is permanently marked with the appropriate CPSC safety label.

EXECUTION:

Lead glass, cushioned by resilient materials, must be free to "float in the opening" (i.e., it

should have adequate clearance around all edges and laterally) so it does not directly touch the framing system.

Obtain compatible glazing sealant or glazing tape, setting blocks and edge blocking material from a local source. If the frame is fire labeled, check with the manufacturer for special glazing requirements. Glass should be set on two identical neoprene, EPDM, silicone or other compatible elastomeric setting blocks. Use spacers inside and out where local practice and job requirements dictate.

Provide edge blocking where local practice requires. Use compatible sealant or glazing tape. Clean only with a soft, non-abrasive cloth.

IMPORTANT - Check glass for damage immediately upon arrival at site.

NOTE: For fire-labeled or safety-glazed openings, special considerations apply. Interpretation of building and fire codes varies depending on locale. Consult with local authorities on the proper fire-rated or safety glazing procedures. Labeled wire glass or ceramic glazing such as Firelite™ must be used in the view window in conjunction with lead glass for labeled openings. LX-57B lead glass is available in a laminated form for safety glazing applications.

PROPERTIES	Lead Glass Type
	20LG
Thickness (mm) (Approx.)	20mm
Thickness (in.) (Approx.)	13/16"
Max. Lead Equivalent (mm)	3.0mm
Max. Lead Equivalent (in.)	7/64"
Densities (gm/cm)	4.36
Weight (lbs/sq.ft)	15.5
X-Ray Peak Voltage (kv)	200
Refractive Index (Typ.)	1.79
Transmission (500 - 600nm)	87.8%
SIZE AND TOLERANCE:	
Minimum size	any size on request
Maximum size	96" x 48" (2438.4mm x 1219.2 mm)



268 Old Lindale Road
Rome, Georgia 30161

Phone Toll Free: 800-329-5323
 Fax Toll Free: 800-329-5320
 e-mail: alshield@alshielding.com
 Internet: www.alshielding.com

Specification — Premium Safety Radiation Shielding Glass

— 1/8" (3.3mm) max lead equivalency

Lead glass is available in a variety of radiation shielding levels and serves as a viewing medium where clear visibility of the treatment area is required.

Laminated Lead Glass - Premium Safety Glazing

GENERAL:

Laminated lead glass is used to allow viewing the patient area while radiation is present and where a safety label is required by the application. The material is placed in a lead shielded frame to hold it in place in the wall.

PRODUCT DETAILS:

Lead Glass is a lead barium glass with more than 60 percent heavy metal oxide including at least 55 percent lead oxide (PbO). This glass is laminated to a 3mm layer of float glass using a PVB interlayer. This allows the glass to be shatter resistant.

It meets Federal Standard DD-G-451, Type 1, ANSI Z97.1-1984 and 16CFR1201 Cat. II. Both glass surfaces are mirror polished. This special quality glass is well-qualified to meet the high standards of stringent safety regulations established in the medical, scientific, as well as nuclear fields around the world.

This glass is permanently marked with the appropriate CPSC safety label.

EXECUTION:

Lead glass, cushioned by resilient materials, must be free to "float in the opening" (i.e., it

should have adequate clearance around all edges and laterally) so it does not directly touch the framing system.

Obtain compatible glazing sealant or glazing tape, setting blocks and edge blocking material from a local source. If the frame is fire labeled, check with the manufacturer for special glazing requirements. Glass should be set on two identical neoprene, EPDM, silicone or other compatible elastomeric setting blocks. Use spacers inside and out where local practice and job requirements dictate.

Provide edge blocking where local practice requires. Use compatible sealant or glazing tape. Clean only with a soft, non-abrasive cloth.

IMPORTANT - Check glass for damage immediately upon arrival at site.

NOTE: For fire-labeled or safety-glazed openings, special considerations apply. Interpretation of building and fire codes varies depending on locale. Consult with local authorities on the proper fire-rated or safety glazing procedures. Labeled wire glass or ceramic glazing such as Firelite™ must be used in the view window in conjunction with lead glass for labeled openings. LX-57B lead glass is available in a laminated form for safety glazing applications.

PROPERTIES	Lead Glass Type
	22LG
Thickness (mm) (Approx.)	22mm
Thickness (in.) (Approx.)	7/8"
Max. Lead Equivalent (mm)	3.3mm
Max. Lead Equivalent (in.)	1/8"
Densities (gm/cm)	4.36
Weight (lbs/sq.ft)	17.0
X-Ray Peak Voltage (kv)	200
Refractive Index (Typ.)	1.79
Transmission (500 - 600nm)	87.8%
SIZE AND TOLERANCE:	
Minimum size	any size on request
Maximum size	96" x 48" (2438.4mm x 1219.2 mm)



268 Old Lindale Road
Rome, Georgia 30161

Phone Toll Free: 800-329-5323
Fax Toll Free: 800-329-5320
e-mail: alshield@alshielding.com
Internet: www.alshielding.com

Specification — Safety Radiation Shielding Glass - 1/16" (1.6mm) max lead eq.

Lead glass is available in a variety of radiation shielding levels and serves as a viewing medium where clear visibility of the treatment area is required.

Laminated Lead Glass - Safety Glazing

GENERAL:

Laminated lead glass is used to allow viewing the patient area while radiation is present and where a safety label is required by the application. The material is placed in a lead shielded frame to hold it in place in the wall.

PRODUCT DETAILS:

Lead Glass is a lead barium glass with more than 60 percent heavy metal oxide including at least 55 percent lead oxide (PbO). This glass is laminated to a 3mm layer of float glass using a PVB interlayer. This allows the glass to be shatter resistant.

It meets Federal Standard DD-G-451, Type 1, ANSI Z97.1-1984 and 16CFR1201 Cat. II. Both glass surfaces are mirror polished. This special quality glass is well-qualified to meet the high standards of stringent safety regulations established in the medical, scientific, as well as nuclear fields around the world.

This glass is permanently marked with the appropriate CPSC safety label.

EXECUTION:

Lead glass, cushioned by resilient materials, must be free to "float in the opening" (i.e., it

should have adequate clearance around all edges and laterally) so it does not directly touch the framing system.

Obtain compatible glazing sealant or glazing tape, setting blocks and edge blocking material from a local source. If the frame is fire labeled, check with the manufacturer for special glazing requirements. Glass should be set on two identical neoprene, EPDM, silicone or other compatible elastomeric setting blocks. Use spacers inside and out where local practice and job requirements dictate.

Provide edge blocking where local practice requires. Use compatible sealant or glazing tape. Clean only with a soft, non-abrasive cloth.

IMPORTANT - Check glass for damage immediately upon arrival at site.

NOTE: For fire-labeled or safety-glazed openings, special considerations apply. Interpretation of building and fire codes varies depending on locale. Consult with local authorities on the proper fire-rated or safety glazing procedures. Labeled wire glass or ceramic glazing such as Firelite™ must be used in the view window in conjunction with lead glass for labeled openings. LX-57B lead glass is available in a laminated form for safety glazing applications.

PROPERTIES	Lead Glass Type	
	12LG	
Thickness (mm) (Approx.)	12mm	
Thickness (in.) (Approx.)	1/2"	
Max. Lead Equivalent (mm)	1.6mm	
Max. Lead Equivalent (in.)	1/16"	
Densities (gm/cm)	4.36	
Weight (lbs/sq.ft)	8.8	
X-Ray Peak Voltage (kv)	150	
Refractive Index (Typ.)	1.79	
Transmission (500 - 600nm)	87.8%	
SIZE AND TOLERANCE:		
Minimum size	any size on request	
Maximum size	96" x 48" (2438.4mm x 1219.2 mm)	



268 Old Lindale Road
Rome, Georgia 30161

Phone Toll Free: 800-329-5323
Fax Toll Free: 800-329-5320
e-mail: alshield@alshielding.com
Internet: www.alshielding.com